


DIANA



Avocado



Bone



Boudoir




Celadon




Feather




Flax



Gold



Griffin



Horizon




Ice



Marble



Metal




Pear




Pearl



Petal



Pewter




Sage



Silver



Steel



Storm








Terra





Diana D14191 Zepel FibreGuard

Brand	Zepel FibreGuard	Composition	100% Recycled Polyester	Martindale	40,000 Martindale Cycles
Collection	—	Width	140cm / 55.1"	Wyzenbeek	100,000 Wyzenbeek Double Rubs
Country of Origin	Asia	Weight	680.4g/m / 622g/yd	Colourfastness	UV 4/8 Blue Scale
Finishes	Backing	Horizontal Repeat	—	Fire Retardancy	CAL 117: 2013, MVSS 302, NFPA 260 (Class 1), BS5852 Source 0
		Vertical Repeat	—	Environmental	Oekotex 100, ISO 14001, Eco

Care Instructions

 Do not bleach	 Do not tumble dry	 Do not wash
 Drycleaning Gentle cycle	 Low iron max 110C	Spot clean with water based detergent

Usage

 Upholstery	 Accessory	 Top of Bed
---	---	--

Attributes

Eco
Fibreguard

Washable 60C

Recycled

WARWICK

Copeland

Collection(s)	Gladiator 4 Book, Copeland, Koppal
Colour(s)	Bark, Birch, Brick, Charcoal, Cloud, Denim, Dusk, Ecru, Eucalyptus, Frost, Granite, Greenstone, Gull, Hazel, Honey, Hunter, Ink, Ivory, Lagoon, Mallard, Marl, Mist, Olive, Onyx, Opal, Praline, Pumice, Raisin, Rosebud, Snow, Spruce, Sumac
Product Type(s)	Upholstery (Heavy Commercial)
Attributes	Halo Easy Care, Washable, Oekotex Standard 100
Styles	Plain, Texture, Modern, Industrial
Composition	100% Polyester
Pattern Match	No
Pattern Repeat (cm)	Plain

Test Results

Wyzenbeek (ASTM D3597, mesh, 4lb/3lb)	100,000 Cycles
Seam Slippage (mm) (ISO 13936-2, Load 180)	Warp 3.1, Weft 3.6
Pilling Resistance (ISO 12945-2)	5
Colourfastness to Light Xenon arc (ISO 105-B02, blue std 6)	5
Colourfastness to Rubbing (ISO 105-X12)	Dry 5, Wet 4/5
Free and Hydrolysed Formaldehyde (ISO 14184-1:1998)	Not Detectable
Flammability AS/NZS 1530.3 - 1999	
Ignitability (0-20)	12
Spread of Flame (0-10)	0
Heat Involved (0-10)	2
Smoke Developed (0-10)	4
Oekotex Standard 100	SH015 133029 TESTEX