## LA CASA LEATHER



SPECIFICATIONS		LA CASA		
Performance		Heavy Commercial		
Warranty		3 Years		
Care		Please use commercially available leather care products, used in accordance with care label instructions.		
Animal Source		Bovine		
Origin		Tanned in Italy		
Туре		Surface grain, lightly buffed, pigmented and embossed.		
Thickness		0.9mm - 1.1mm		
Average Hide Size		4.2 - 4.4m <sup>2</sup>		
Rubfastness		Marring	Transfer	Results
(grey scale grade) EN ISO 11640 (SLF450)	Dry 500	4/5	4/5	Pass
	Wet 250	4	4	Pass
	Sweat 80	4/5	4/5	Pass
Fastness to Light (Blue wool rating) EN ISO 11644 (IUF470)		>5		Pass
Finish Adhesion (N/cm) EN ISO 11644 (IUF470)	Along	8.8		Pass
	Across	8.8		Pass
	Average	8.8		Pass
Flex Endurance (50,000 cycles) EN ISO 5402 (IUF20)		No cracks at 50,000 cycles		Pass
Tear Strength ISO 3377-1	Along	67		Pass
	Across	62		Pass
	Average	64		Pass
pH EN ISO 4045 (IUC 11)		4.82		Pass
Formaldehyde ISO 17226-1		13ррт		Pass
Flammabilty IMO RESOLUTION A.652 (16)		Pass		
Flammabilty AS1530.3	Ignitability	15		
	Spread of Flame	0		
	Heat Evolved	3		
Please Note: Median test results displayed base	Smoke Developed	4		

Please Note: Median test results displayed based off results from light, medium, & dark hides.